

RUST GRIP

Incineration Plant Ducts Korea

I am sending you RG application pictures on filtration ducts in an incineration plant for your reference. Previously, RG+LK(red) was applied in the same facility. But as the oxidation level was not as high as initially thought, RG was applied twice without using LK as the top coat.

Filtration Duct Interior Coating

Date	October 14, 2006	Customer	Ecoentop
Application Area	- Interior of SDR Filtration Collector Ducts - 6mm Steel		
Purpose	Corrosion Prevention		
Application Method	Removed moisture with MEK Applied Rust Grip two times (Ave. 200~250microns)		
Application Pictures	 <p><Ducts></p>  <p><Duct 1 before coatings></p>  <p><Duct 2 before coatings></p>  <p><Magnified View></p>  <p><1st Application of RustGrip></p>  <p><RustGrip after 1st coating></p>		



<2nd application of RustGrip>



< RustGrip after 2nd coating>



<Filtration Interior facility after coating>